



CFE03320WOUS  
(CFE3320US)

CFE3320US.02/04

DECLARATION

I, Ryuichi YAMADA, a Japanese Patent Attorney registered No. 7898 having my Business Office at Hasegawa Bldg., 4F, 7-7 Toranomom 3-chome, Minato-ku, Tokyo, Japan, solemnly and sincerely declare:

That I have a thorough knowledge of Japanese and English languages; and

That the attached pages contain a correct translation into English of the specification of the following Japanese Application:

<u>APPLICATION</u>	<u>DATE OF</u>
<u>NUMBER</u>	<u>APPLICATION</u>
064205/2001(Pat.)	8/MAR/2001

Applicant(s)  
CANON KABUSHIKI KAISHA

Signed this 20th day of September, 2005.

Ryuichi YAMADA

PATENT OFFICE  
JAPANESE GOVERNMENT

This is to certify that the annexed is a true copy of the  
following application as filed with this Office.

<u>APPLICATION NUMBER</u>	<u>DATE OF APPLICATION</u>
064205/2001(Pat.)	8/MAR/2001

Applicant(s)  
CANON KABUSHIKI KAISHA

11/NOV/2003

Director-General,  
Patent Office : YASUO IMAI (Seal)

Certificate No. 3092895/2003

CFE3320US.02/03

<FILE NO.> 4423028

-----  
<DOCUMENT> PATENT APPLICATION

<FILE NO.> 4423028

<FILING DATE> 8/MAR/2001

<DIRECTED TO> The Director General of the Patent Office

<INTERNATIONAL CLASSIFICATION> H05B 33/00

<TITLE OF THE INVENTION> LUMINESCENCE DEVICE AND  
DISPLAY APPARATUS

<NUMBER OF CLAIMS> 7

<INVENTOR(S)>

<Address> c/o CANON KABUSHIKI KAISHA  
3-30-2 Shimomaruko, Ohta-ku, Tokyo

<Name> Jun KAMATANI

<Address> Ditto

<Name> Takao TAKIGUCHI

<Address> Ditto

<Name> Akira TSUBOYAMA

<Address> Ditto

<Name> Manabu FURUGORI

<Address> Ditto

<Name> Seishi MIURA

<Address> Ditto

<Name> Takashi MORIYAMA

<Address> Ditto

<Name> Shinjiro OKADA

<Address> Ditto

<Name> Koji NOGUCHI

<APPLICANT>

<IDENTIFICATION NO.> 000001007

<NAME> CANON KABUSHIKI KAISHA

<ATTORNEY>

<IDENTIFICATION NO.> 100096828

<PATENT ATTORNEY>

<NAME> Keisuke WATANABE

<TEL> 03-3501-2138

<DESIGNATED ATTORNEY>

<IDENTIFICATION NO.> 100059410

<PATENT ATTORNEY>

<NAME> Yoshio TOYODA

<TEL> 03-3501-2138

<DESIGNATED ATTORNEY>

<IDENTIFICATION NO.> 100110870

<PATENT ATTORNEY>

<NAME> Yoshihiro YAMAGUCHI

<TEL> 03-3501-2138

<CLAIM FOR PRIORITY>

<APPLICATION NO.> 364650/2000(PAT.)

<FILING DATE> 30/NOV/2000

<OFFICIAL FEES>

<PREPAY REGISTRATION NO.> 004938

<AMOUNT> 21,000YEN

<ARTICLES PRESENTED>

<ARTICLE> Specification 1

<ARTICLE> Drawing(s) 1

<ARTICLE> Abstract 1

<GENERAL POWER NO.> 0101029

<REQUEST FOR PROOF> YES

[Document]


Specification

[Title of the Invention]

Luminescence Device and Display Apparatus




[Claims]

1. A luminescence device having a layer containing a metal coordination compound, which is represented by formula (1) below:



wherein M is a metal atom of Ir, Pt, Rh or Pd; L and L' are mutually different bidentate ligands; m is 1, 2 or 3 and n is 0, 1 or 2 with the proviso that m+n is 2 or 3; a partial structure ML<sub>m</sub> is represented by formula (2) shown below and a partial structure ML'<sub>n</sub> is represented by formula (3) or (4) shown below:

<KA-1>



wherein N and C are independently a nitrogen atom and a carbon atom; A and A' are each cyclic group capable of having an optional substituent, including a


nitrogen atom and bonded to the metal atom M via the nitrogen atom; B and B' are each cyclic group capable of having an optional substituent, including a carbon atom and bonded to the metal atom M via the carbon atom; {(the optional substituent of the cyclic groups is selected from a halogen atom, cyano group, a nitro group, a trialkylsilyl group (of which the alkyl groups are independently a linear or branched alkyl group having 1 to 8 carbon atoms), a linear or branched alkyl group having 1 to 20 carbon atoms of (which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with -O-, -S-, -CO-, -CO-O-, -O-CO-, -CH=CH- or -C=C-, and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom); or an aromatic group capable of having an optional substituent that is a halogen atom, a cyano atom, a nitro atom, a linear or branched alkyl group having 1 to 20 carbon atoms (of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with -O-, -S-, -CO-, -CO-O-, -O-CO-, -CH=CH- or -C=C-, and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom))};

the cyclic groups A and B are bonded to each other via a covalent bond and the cyclic group A' and B' are bonded to each other via a covalent bond;

E and G are independently a linear or branched alkyl group having 1 to 20 carbon atoms of which the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom, or an aromatic cyclic group capable of having an optional substituent (that is a halogen atom, a cyano atom, a nitro atom, a trialkylsilyl group of which the alkyl groups are independently a linear or branched alkyl group having 1 - 8 carbon atoms, a linear or branched alkyl group having 1 to 20 carbon atoms of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with -O-, -S-, -CO-, -CO-O-, -O-CO-, -CH=CH- or -C≡C-, and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom; and

at least one of the optional substituents of the cyclic groups, and the cyclic groups B and B' include an aromatic cyclic group capable of having an optional substituent represented by the following formula (5):

<KA-2>



the optional substituent of the aromatic cyclic group is selected from a halogen atom, cyano group, a nitro group, a trialkylsilyl group of which the alkyl groups

are independently a linear or branched alkyl group having 1 to 8 carbon atoms, a linear or branched alkyl group having 1 to 20 carbon atoms of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with -O-, -S-, -CO-, -CO-O-, -O-CO-, -CH=CH- or -C=C-; and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom, or an aromatic group capable of having an optional substituent (that is a halogen atom, a cyano atom, a nitro atom, a linear or branched alkyl group having 1 to 20 carbon atoms of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with -O-, -S-, -CO-, -CO-O-, -O-CO-, -CH=CH- or -C=C-, and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom) with the proviso that one or two carbon atoms in said formula (5) can be optionally replaced with a nitrogen atom, and with the proviso that an adjacent pair of optional substituents can be bonded to form a cyclic structure.

2. A luminescence device according to Claim 1, wherein a partial structure ML'n in said formula (1) is represented by said formula (3).

3. A luminescence device according to Claim 1,



wherein a partial structure ML'n in said formula (1) is represented by said formula (4).

4. A luminescence device according to Claim 1, wherein n in said formula (1) is 0.

5. A luminescence device according to any one of Claims 1 to 4, wherein the cyclic group B in said formula (1) comprises an isoquinoline skeleton.

6. A luminescence device according to any one of Claims 1 to 5, wherein the organic layer including said metal coordination compound comprises an electric-field luminescence device between a pair of oppositely disposed electrodes comprising a transparent electrode (anode) and a metal electrode (cathode) which are supplied with a voltage to cause luminescence.

7. A display apparatus, comprising a luminescence device as defined in any one of Claims 1 to 6, as a display device.

[Detailed Description of the Invention]

[Field]

The present invention relates to a luminescence device using an organic compound. More

particularly, the invention relates to an organic electroluminescence device (also called an organic EL device) by use of a metal coordination compound represented by formula (1) appearing hereinafter, as a luminescence material.

[Prior Art]

An extensive study for an organic EL device formation as a luminescence device of a high-speed responsiveness and a high efficiency, has been conducted. The basic structure of the organic EL device is illustrated in Figures 1A and 1B (for example, Macromol. Symp. 125, 1 - 48 (1997)).

As described in Figure 1, an organic EL device generally comprises, on a transparent substrate 15, a transparent electrode 14, a plurality of organic film layers and a metal electrode 11 formed so as to cover the organic layers.

Referring to Figure 1A, the organic layer comprises a luminescence layer 12 and a hole-transporting layer 13. The transparent electrode 14 may comprises ITO or the like, having a large work function so as to facilitate hole injection from the transparent electrode 14 to the hole-transporting layer 13. The metal electrode 11 comprises a metal material having a small work function, such as aluminum, magnesium or alloys of these elements, so as to facilitate electron injection into the organic

luminescence device. The film having the thickness of 50 to 200 nm is used for the electrodes.

In the luminescence layer 12, aluminum quinolinol complex (inclusive of Alq3 shown in the formula (3) as a representative example) having an electron-transporting characteristic and a luminescence characteristic, are used for example. In a hole-transporting layer, a material having an electron-donative property, such as a triphenyldiamine derivative (inclusive of  $\alpha$ -NPD shown in the formula (3) as a representative example), is used for example.

A device organized above exhibits a current-rectifying characteristic, and when an electric field is applied between the metal electrode 11 as a cathode and the transparent electrode 14 as an anode, electrons are injected from the metal electrode 11 into the luminescence layer 12, and holes are injected from the transparent electrode 15.

The injected holes and electrons are recombined in the luminescence layer 12 to form excitons, which cause luminescence. In this instance, the hole-transporting layer 13 functions as an electron-blocking layer to increase the recombination efficiency at the boundary between the luminescence layer layer 12 and the hole-transporting layer 13, thereby providing an enhanced luminescence efficiency.

Further, in the structure of Figure 1(b), an electron-transporting layer 16 is disposed between the metal electrode 11 and the luminescence layer 12 in Figure 1(a). As a result, the luminescence function is separated from the functions of electron transportation and hole transportation to provide a structure exhibiting more effective carrier blocking, thus increasing the luminescence efficiency. The electron-transporting layer 16, may comprise, e.g., an oxadiazole derivative.

In ordinary organic EL devices, fluorescence caused during a transition of luminescent center molecule from a single excited state to a ground state is used as luminescence. On the other hand, not the above fluorescence (luminescence) via singlet exciton, phosphorescence (luminescence) via triplet exciton has been studied for use in organic EL devices as described in, e.g., "Improved energy transfer in electrophosphorescent device" (D.F. O'drien et al., Applied Physics Letters. Vol. 74, No. 3, pp. 442 - 444 (1999)) and "Very high-efficiency green organic light-emitting devices based on electrophosphorescence" (M.A. Baldo et al., Applied Physics Letters, Vol. 75, No. 1, pp. 4 - 6 (1999)).

The EL devices shown in these documents may generally have a sectional structure shown in Figure 1C. Referring to Figure 1C, four organic layers

including a hole transfer layer 13, a luminescence layer 12, and exciton diffusion-prevention layer 17, and an electron transport layer 16 are successively formed in this order on the transparent electrode (anode) 14. The materials used therein include carrier-transporting materials and phosphorescent materials which is represented in KA-3, of which the names and structures are shown below together with their abbreviations.

Alq3: aluminum-quinolinol complex,


$\alpha$ -NPD: N4,N4'-di-naphthalene-1-yl-N4,N4'-diphenyl-biphenyl-4,4'-diamine,

CBP: 4,4'-N,N'-dicarbazole-biphenyl,


BCP: 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline,

PtOEP: platinum-octaethyl porphine complex,  
and


Ir(ppy)<sub>3</sub>: iridium-phenylpyridine complex.




Alq3




$\alpha$ -NPD



CBP



BCP



Ir(ppy)<sub>3</sub>

The above-mentioned Articles 1 and 2 both have reported structures, as exhibiting a high efficiency, including a hole-transporting layer 13 comprising  $\alpha$ -NPD, an electron-transporting layer 16 comprising Alq3, an exciton diffusion-preventing layer 17 comprising BCP, and a luminescence layer 12 comprising CBP as a host and ca. 6 % of PtOEP or Ir(ppy)<sub>3</sub> as a phosphorescent material dispersed in mixture therein.

Such a phosphorescent material is particularly noted at present because it is expected to provide a high luminescence efficiency in principle for the following reasons. More specifically, excitons formed by carrier recombination comprise

singlet excitons and triplet excitons in a probability ratio of 1:3. Conventional organic EL devices have utilized fluorescence caused by the transition of a singlet exciton to a ground state, of which the luminescence efficiency is limited to at most 25 %. On the other hand, if phosphorescence generated from triplet excitons is utilized, an efficiency of at least three times is expected, and even an efficiency of 100 %, i.e., four times, can be expected in principle, if a transition owing to intersystem crossing from a singlet state having a higher energy to a triplet state is taken into account.

The use of phosphorescence based on transition from the triplet excited state has also been proposed in, e.g., Japanese Laid-Open Patent Application No. HEI-11-329739 (organic EL device and manufacturing method for organic EL device), Japanese Laid-Open Patent Application No. HEI-11-256148 (luminescence material and organic EL device using the luminescence material) and HEI-8-319482 (organic electroluminescence device).

[Problems to be Solved]

However, the above-mentioned organic EL devices utilizing phosphorescence have accompanied with a problem of the deterioration of luminescence efficiency and device stability. The reason for luminescent deterioration has been clarified as yet

but may be attributable to such a phenomenon that the life of triplet exciton is generally longer than that of single exciton by at least three digits, so that molecule is placed in a higher-energy state for a long period to cause reaction with ambient substance, formation of exciplex or excimer, change in minute molecular structure, structural change of ambient substance or the like.

A luminescent center material used in a phosphorescent luminescence device is desired to exhibit high luminescence efficiency and show a high stability.

Accordingly, it is a principal object of the present invention to provide a luminescence device which exhibits a high luminescence efficiency and retains a high luminance for a long period, and having a luminescence wavelength of long-wavelength region, and a display device using the luminescence device.

[Means for Solving the Problems]

More specifically, in accordance with a principal aspect of the present invention, there is provided a luminescence device having a layer containing a metal coordination compound, which is represented by the formula (1) shown below:




wherein M is a metal atom of Ir, Pt, Rh or Pd; L and L' are mutually different bidentate ligands; m is 1, 2



or 3 and n is 0, 1 or 2 with the proviso that m+n is 2 or 3; a partial structure  $ML_m$  is represented by formula (2) shown below and a partial structure  $ML'_n$  is represented by formula (3) or (4) shown below:

<KA-4>



N and C are independently a nitrogen atom and a carbon atom; A and A' are each cyclic group capable of having an optional substituent, including a nitrogen atom and bonded to the metal atom M via the nitrogen atom; B and B' are each cyclic group capable of having an optional substituent, including a carbon atom and bonded to the metal atom M via the carbon atom; {(the optional substituent of the cyclic groups is selected from a halogen atom, cyano group, a nitro group, a trialkylsilyl group (of which the alkyl groups are independently a linear or branched alkyl group having 1 to 8 carbon atoms), a linear or branched alkyl group having 1 to 20 carbon atoms (of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with -O-, -S-, -C-O-, -CO-O-, -O-CO-, -CH=CH-

or  $\text{-C}\equiv\text{C-}$ , and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom); or an aromatic group capable of having an optional substituent that is a halogen atom, a cyano atom, a nitro atom, a linear or branched alkyl group having 1 to 20 carbon atoms (of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with  $\text{-O-}$ ,  $\text{-S-}$ ,  $\text{-CO-}$ ,  $\text{-CO-O-}$ ,  $\text{-O-CO-}$ ,  $\text{-CH=CH-}$  or  $\text{-C}\equiv\text{C-}$ , and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom));


The cyclic groups A and B are bonded to each other via a covalent bond and the cyclic groups A' and B' are bonded to each other via a covalent bond.

E and G are independently a linear or branched alkyl group having 1 to 20 carbon atoms (of which the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom), or an aromatic cyclic group capable of having an optional substituent (that is a halogen atom, a cyano atom, a nitro atom, a trialkylsilyl group of which the alkyl groups are independently a linear or branched alkyl group having 1 - 8 carbon atoms), a linear or branched alkyl group having 1 to 20 carbon atoms (of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with  $\text{-O-}$ ,  $\text{-S-}$ ,  $\text{-CO-}$ ,  $\text{-CO-O-}$ ,  $\text{-O-CO-}$ ,  $\text{-CH=CH-}$  or  $\text{-C}\equiv\text{C-}$ , and the

alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom)).

At least one of the optional substituents of the cyclic groups, and the cyclic groups B and B' include an aromatic cyclic group capable of having an optional substituent represented by the following formula (5):

<KA-5>



The optional substituent of the aromatic cyclic group is selected from a halogen atom, cyano group, a nitro group, a trialkylsilyl group of which the alkyl groups are independently a linear or branched alkyl group having 1 to 8 carbon atoms, a linear or branched alkyl group having 1 to 20 carbon atoms of which the alkyl group can include one or non-neighboring two or more methylene groups that can be replaced with -O-, -S-, -CO-, -CO-O-, -O-CO-, -CH=CH- or -C≡C-; and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom, or an aromatic group capable of having an optional substituent (that is a halogen atom, a cyano atom, a nitro atom, a linear or branched alkyl group having 1 to 20 carbon atoms of which the alkyl group can include one or non-neighboring two or more

methylene groups that can be replaced with -O-, -S-, -CO-, -CO-O-, -O-CO-, -CH=CH- or -C≡C-, and the alkyl group can include a hydrogen atom that can be optionally replaced with a fluorine atom) with the proviso that one or two carbon atoms in the formula (5) can be optionally replaced with a nitrogen atom, and with the proviso that an adjacent pair of optional substituents can be bonded to form a cyclic structure.

A luminescence device according to the present invention may be preferable that a partial structure ML'n is represented by the formula (3) in the formula (1). A luminescence device according to the present invention may be preferably that a partial structure ML'n in the formula (1) is represented by the formula (4) in the formula (1). A luminescence device according to the present invention may be preferable that n is 0 in the formula (1).

A luminescence device according to the present invention may be preferable that the cyclic group B in the isoquinoline skeleton in the formula (1).

The luminescence device may preferably that the organic layer comprising the metal coordination compound comprises an electric-field luminescence device between a pair of oppositely disposed electrodes comprising a transparent electrode (anode) and a metal electrode (cathode) which are supplied

with a voltage to cause luminescence.

In accordance with a further aspect of the present invention, there is provided a display apparatus, comprising a luminescence device described above, as a display device.

[Description of the Preferred Embodiments]

In the case where the luminescence layer comprises a host material having a carrier-transporting function and a phosphorescent guest material, a process of phosphorescence via triplet excitons may include unit processes as follows:

1. transportation of electrons and holes within a luminescence layer,
2. formation of host excitons,
3. excitation energy transfer between host molecules,
4. excitation energy transfer from the host to the guest,
5. formation of guest triplet excitons, and
6. transition of the guest triplet excitons to the ground state and phosphorescence.

Desirable energy transfer in each unit process and luminescence are caused in competition with various energy deactivation processes.

Needless to say, a luminescence efficiency of an EL device is increased by increasing the luminescence quantum yield of a luminescence center

material. In addition thereto, an efficiency energy transfer between host material molecules and/or between host material molecule and guest material molecule is also an important factor. Further, the above-described luminescent deterioration in energized state may presumably relate to the luminescent center material per se or an environmental change thereof by its ambient molecular structure.

As a result of various studies of inventors, it has been found that an organic EL device using the metal coordination compound of the formula (1) as a principal luminescence material exhibits high-efficiency luminescence and has a luminescence wavelength of long-wavelength region, retains high luminance for a long period.

It is preferable that a partial structure ML'n of metal coordination compounds represented in the formula (1) is represented by the formula (3), that a partial structure ML'n is represented by the formula (4), and that n is 0 in the formula (1). Further, it is preferable that the cyclic group B is the isoquinolyl skeleton in the formula (1).

The metal coordination compound used in the present invention emits phosphorescence, and its lowest excited state is believed to be an MLCT\* (metal-to-ligand charge transfer) excited state in a triplet state, and phosphorescence is caused at the

time of transition from such a state to the ground state.

The luminescence material exhibited high phosphorescence quantum yields of 0.15 to 0.9 and short phosphorescence lives of 1 to 30  $\mu$ sec. A short phosphorescence life becomes a condition for causing little energy deactivation and exhibiting an enhanced luminescence efficiency. More specifically, if the phosphorescence life is long, the number of triplet state molecules maintained for luminescence is increased, and the deactivation process is liable to occur, thus resulting in a lower luminescence efficiency particularly at the time of a high-current density. The material of the present invention is suitable as a luminescence material for an EL device having a high phosphorescence quantum yield and a short phosphorescence life. Further, by introducing an isoquinoline skeleton in a metal coordination compound having a structure of a type represented by the above formula (1), the luminescence wavelength can be adjusted, and it has been found that the metal coordination compound of the present invention wherein the isoquinoline skeleton is bonded to the cyclic group A at its position-1, is unexpectedly advantageous for increasing the luminescence wavelength. From this fact, a metal coordination compound of the present invention is suited as a

luminescence material for an EL device.

In an actual current conduction test, the luminescence material of the present invention, i.e., a metal coordination compound having a ligand comprising an isoquinoline skeleton bonded to a cyclic group A at its 1-position, showed a high stability.

It is believed that the ligand of the present invention, as a result of introduction of isoquinoline skeleton, has a rigid molecular structure, so as to suppress the formation of an excitation-associated molecule resulting in thermal deactivation, thus suppressing energy deactivation due to molecular movement. Further, it is also believed that extinction processes are reduced to result in an improve device performance. Accordingly, a luminescence material having a luminescence wavelength of long-wavelength region (red luminescence) and a high chemical stability as well as a high luminescence efficiency has not been realized heretofore but can be realized by the luminescence material of the present invention.

The luminescence device may preferably that the organic layer including the metal coordination compound represented by the formula (1) comprises an electric-field luminescence device between a pair of oppositely disposed electrodes comprising a transparent electrode (anode) and a metal electrode



(cathode) which are supplied with a voltage to cause luminescence.

The luminescence device having a high efficiency of the present invention is applicable to the product which requires for energy saving and high luminosity. As an example of application, the light source of a display apparatus and an illumination apparatus or printer, the back light of a liquid crystal display apparatus or the like, can be considered. As for a display apparatus, energy saving, and high visibility and a light flat panel display are provided. As for a light source of a printer, the laser light source of the laser beam printer used widely can be transposed to the luminescence device. The device which can carry out an address independently is disposed on an array, and image formation is performed by performing a desired exposure process to the photosensitive drum. By using the device of the present invention, the volume of the apparatus can be decreased sufficiently. The energy saving effect according to the present invention is expected regarding the illumination apparatus and back light.

Hereinbelow, an embodiment of using a device of the present invention in combination with an active matrix substrate is briefly described with reference to Figures 4 to 6.

Figure 4 illustrates an embodiment of panel structure comprising an EL device and drive means. The panel is provided with a scanning signal driver, a data signal driver and a current supply source which are connected to gate selection lines, data signal lines and current supply lines, respectively. At each intersection of the gate selection lines and the data signal lines, a display pixel electrode is disposed. The scanning signal drive sequentially selects the gate selection lines G1, G2, G3 ... Gn, and in synchronism herewith, picture signals are supplied from the data signal driver to display a printer.

Next, the operation of a pixel electrode will be described. In the pixel electrode, when the selection signal is supplied to a gate selection line, TFT1 is set to being turned on, and a picture signal is supplied to Cadd, and then, the gate potential of TFT2 is determined. The current is supplied to the EL element through the current supply line according to the gate potential of TFT2. The gate potential of TFT2 is retained Cadd until the next scan is performed for TFT1, so that the EL element is held at Cadd until next scanning selection of the TFT1 is carried out, and therefore, the luminescence can be emitted during one frame period.

Figure 6 is a schematic view of an example of a sectional structure of TFT substrate to be used

for the present invention. A p-Si layer is provided on a glass layer. The impurities respectively required for the regions of channel, a drain, and a source are doped. The gate electrode is provided through the gate insulator, and simultaneously, the drain electrode and source electrode connected to the drain region and the source region are formed. The insulator layer and the ITO electrode as the pixel electrode are accumulated on the drain electrode and the source electrode. The ITO electrode is connected to the drain electrode through a contact hole.

The present invention is not limited to the switching device, however, it may be also applicable easily to a substrate of a single crystal silicone, a MIM device or a-Si type element or the like.


A multiplayer or single layer organic EL layer and cathode layer is accumulated one by one on the ITO electrode, and an organic display panel can be provided. By driving a display panel including a luminescence layer comprising a luminescence material of the present invention, it becomes possible to provide a display which exhibits a good picture quality and is stable even for a long period display.

Some synthetic paths for providing a metal coordination compound represented by the above-mentioned formula (1) are illustrated below with reference to an iridium coordination compound, for


example.

Synthetic of ligand L (Reference; Kevin R, et al.,  
Org., Lett., 1999, 1, 553 - 556)

<KA-6>




<KA-7>




<Ka-8>

Synthetic of iridium coordination compound



or



Some specific structural examples of metal coordination compounds used in the present invention are shown in Table 1 to Table 25 appearing hereinafter, which are however only representative examples and are not exhaustive. Ph to Py2 used for Table 1 to Table 25 represent partial structures shown below.

<KA-9>























Table 1










No	M	N	π	A	B	A'	B'	E	G	A-R1	A-R2	A-R1	A-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
1	1	3	0	Ph	1q1	—	—	—	—	H	H	—	—	H	H	H	H	—	—	—	—
2	1	3	0	Ph	1q1	—	—	—	—	Ph	H	—	—	H	H	H	H	—	—	—	—
3	1	3	0	Ph	1q1	—	—	—	—	H	Ph	—	—	H	H	H	H	—	—	—	—
4	1	3	0	Ph	1q1	—	—	—	—	Ph	H	—	—	H	Ph	H	H	—	—	—	—
5	1	3	0	Ph	1q1	—	—	—	—	CH <sub>3</sub>	H	—	—	H	CH <sub>3</sub>	CF <sub>3</sub>	H	—	—	—	—
6	1	3	0	Ph	1q1	—	—	—	—	H	CH <sub>3</sub>	—	—	H	CF <sub>3</sub>	H	H	—	—	—	—
7	1	3	0	Ph	1q1	—	—	—	—		H	—	—	H	H	H	H	—	—	—	—
8	1	3	0	Ph	1q1	—	—	—	—	H		—	—	H	H	H	H	—	—	—	—
9	1	3	0	Ph	1q1	—	—	—	—		H	—	—	H	H	H	H	—	—	—	—
10	1	3	0	Ph	1q1	—	—	—	—	H		—	—	H	H	H	H	—	—	—	—
11	1	3	0	Ph	1q1	—	—	—	—	CF <sub>3</sub>	H	—	—	H	H	H	H	—	—	—	—
12	1	3	0	Ph	1q1	—	—	—	—	H	CF <sub>3</sub>	—	—	H	H	H	H	—	—	—	—
13	1	3	0	Ph	1q1	—	—	—	—		H	—	—	H	H	H	H	—	—	—	—
14	1	3	0	Ph	1q1	—	—	—	—	H		—	—	H	H	H	H	—	—	—	—
15	1	3	0	Ph	1q1	—	—	—	—		H	—	—	H	H	H	H	—	—	—	—
16	1	3	0	Ph	1q1	—	—	—	—		H	—	—	H	H	H	H	—	—	—	—
17	1	3	0	Ph	1q1	—	—	—	—	OCH <sub>3</sub>	H	—	—	H	H	H	H	—	—	—	—
18	1	3	0	Ph	1q1	—	—	—	—	H	OCH <sub>3</sub>	—	—	H	H	H	H	—	—	—	—
19	1	3	0	Ph	1q1	—	—	—	—		H	—	—	H	Ph	H	H	—	—	—	—
20	1	3	0	Tn1	1q1	—	—	—	—	H	H	—	—	H	H	H	H	—	—	—	—

Table 2







No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
21	1	3	0	Tn1	1q1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
22	1	3	0	Tn1	1q1	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
23	1	3	0	Tn1	1q1	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
24	1	3	0	Tn1	1q1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-
25	1	3	0	Tn1	1q1	-	-	-	-	H	CH3	-	-	H	H	H	H	-	-	-	-
26	1	3	0	Tn1	1q1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
27	1	3	0	Tn1	1q1	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
28	1	3	0	Tn1	1q1	-	-	-	-	CH3	H	-	-	H	H	H	CF3	-	-	-	-
29	1	3	0	Tn1	1q1	-	-	-	-	OCH3	H	-	-	H	H	H	H	-	-	-	-
30	1	3	0	Tn1	1q1	-	-	-	-	H	OCH3	-	-	H	H	H	H	-	-	-	-
31	1	3	0	Tn1	1q1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
32	1	3	0	Tn1	1q1	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
33	1	3	0	Tn1	1q1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
34	1	3	0	Tn1	1q1	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
35	1	3	0	Tn1	1q1	-	-	-	-	H	H	-	-	H		H	H	-	-	-	-
36	1	3	0	Tn1	1q1	-	-	-	-	H	H	-	-	H	H		H	-	-	-	-
37	1	3	0	Tn1	1q1	-	-	-	-	H	H	-	-	H	Ph	H	H	-	-	-	-
38	1	3	0	Tn1	1q1	-	-	-	-	H	H	-	-	H	H	Ph	H	-	-	-	-
39	1	3	0	Tn1	1q1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
40	1	3	0	Tn2	1q1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-



Table 3






No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R8	B'-R3	B'-R4	B'-R5	B'-R8
41	1	3	0	Tn2	1q1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
42	1	3	0	Tn2	1q1	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
43	1	3	0	Tn2	1q1	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
44	1	3	0	Tn2	1q1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-
45	1	3	0	Tn2	1q1	-	-	-	-	H	CH3	-	-	H	H	H	H	-	-	-	-
46	1	3	0	Tn2	1q1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
47	1	3	0	Tn2	1q1	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
48	1	3	0	Tn2	1q1	-	-	-	-	H	H	-	-	CF3	H	H	H	-	-	-	-
49	1	3	0	Tn2	1q1	-	-	-	-		H	-	-	H	H	H	CF3	-	-	-	-
50	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
51	1	3	0	Tn3	1q1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
52	1	3	0	Tn3	1q1	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
53	1	3	0	Tn3	1q1	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
54	1	3	0	Tn3	1q1	-	-	-	-	CH3	H	-	-	H	H	CF3	H	-	-	-	-
55	1	3	0	Tn3	1q1	-	-	-	-	H	CH3	-	-	H	CF3	H	H	-	-	-	-
56	1	3	0	Tn3	1q1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
57	1	3	0	Tn3	1q1	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
58	1	3	0	Tn3	1q1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
59	1	3	0	Tn3	1q1	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
60	1	3	0	Tn3	1q1	-	-	-	-	CF3	H	-	-	H	H	H	H	-	-	-	-

Table 4








No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
61	1	3	0	Tn3	1q1	-	-	-	-	H	CF3	-	-	H	H	H	H	-	-	-	-
62	1	3	0	Tn3	1q1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
63	1	3	0	Tn3	1q1	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
64	1	3	0	Tn3	1q1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
65	1	3	0	Tn3	1q1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
66	1	3	0	Tn3	1q1	-	-	-	-	OCH3	H	-	-	H	H	H	H	-	-	-	-
67	1	3	0	Tn3	1q1	-	-	-	-	H	OCH3	-	-	H	H	H	H	-	-	-	-
68	1	3	0	Tn3	1q1	-	-	-	-		H	-	-	H	Ph	H	H	-	-	-	-
69	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	Ph	H	H	-	-	-	-
70	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	H	Ph	H	-	-	-	-
71	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H		H	H	-	-	-	-
72	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	H		H	-	-	-	-
73	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
74	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
75	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	F	H	H	-	-	-	-
76	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	H	H	F	-	-	-	-
77	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
78	1	3	0	Tn3	1q1	-	-	-	-	H	H	-	-	H	H	H	F	-	-	-	-
79	1	3	0	Tn3	1q1	-	-	-	-	OCH2CH2	H	-	-	H	H	H	H	-	-	-	-
80	1	3	0	Np1	1q1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-

Table 5






No	M	N	n	A	B	A'	B'	E	G	A-R1	A-R2	B-R1	B-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
81	1	3	0	Np1	1q1	-	-	-	-	Ph	H	Ph	H	H	H	-	H	-	-	-	-
82	1	3	0	Np1	1q1	-	-	-	-	H	Ph	H	H	H	H	-	H	-	-	-	-
83	1	3	0	Np1	1q1	-	-	-	-	Ph	H	Ph	H	H	Ph	-	H	-	-	-	-
84	1	3	0	Np1	1q1	-	-	-	-	H	H	H	H	H	H	-	Ph	-	-	-	-
85	1	3	0	Np1	1q1	-	-	-	-	CH3	H	H	H	H	H	-	H	-	-	-	-
86	1	3	0	Np1	1q1	-	-	-	-	H	CH3	H	H	H	H	-	H	-	-	-	-
87	1	3	0	Np1	1q1	-	-	-	-	H	H	H	H	H	CF3	-	H	-	-	-	-
88	1	3	0	Np1	1q1	-	-	-	-	H	H	H	H	H	H	-	H	-	-	-	-
89	1	3	0	Np1	1q1	-	-	-	-	H	H	H	H	CF3	H	-	H	-	-	-	-
90	1	3	0	Np2	1q1	-	-	-	-	H	H	H	H	H	H	-	H	-	-	-	-
91	1	3	0	Np2	1q1	-	-	-	-	Ph	H	H	H	H	H	-	H	-	-	-	-
92	1	3	0	Np2	1q1	-	-	-	-		Ph	-	H	H	H	-	H	-	-	-	-
93	1	3	0	Np2	1q1	-	-	-	-	Ph	H	H	H	H	Ph	-	H	-	-	-	-
94	1	3	0	Np2	1q1	-	-	-	-	CH3	H	H	H	H	H	-	CF3	-	-	-	-
95	1	3	0	Np2	1q1	-	-	-	-	H	CH3	H	H	H	CF3	-	H	-	-	-	-
96	1	3	0	Np2	1q1	-	-	-	-		H	-	H	H	H	-	H	-	-	-	-
97	1	3	0	Np2	1q1	-	-	-	-	H		-	H	H	H	-	H	-	-	-	-
98	1	3	0	Np2	1q1	-	-	-	-		H	-	H	H	H	-	H	-	-	-	-
99	1	3	0	Np2	1q1	-	-	-	-	H		-	H	H	H	-	H	-	-	-	-
100	1	3	0	Np2	1q1	-	-	-	-	CF3	H	-	H	H	H	-	H	-	-	-	-

Table 6








No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
101	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	CF3	-	-	H	H	H	H	-	-	-	-
102	Ir	3	0	Nb2 Iq1	-	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
103	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
104	Ir	3	0	Nb2 Iq1	-	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
105	Ir	3	0	Nb2 Iq1	-	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
106	Ir	3	0	Nb2 Iq1	-	-	-	-	-	OCH3	H	-	-	H	H	H	H	-	-	-	-
107	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	OCH3	-	-	H	H	H	H	-	-	-	-
108	Ir	3	0	Nb2 Iq1	-	-	-	-	-		H	-	-	H	Ph	H	H	-	-	-	-
109	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	Ph	H	H	-	-	-	-
110	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	H	Ph	H	-	-	-	-
111	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H		H	H	-	-	-	-
112	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	H		H	-	-	-	-
113	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
114	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
115	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	F	H	H	-	-	-	-
116	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	F	H	F	-	-	-	-
117	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	F	H	H	H	-	-	-	-
118	Ir	3	0	Nb2 Iq1	-	-	-	-	-	H	H	-	-	H	H	F	H	-	-	-	-
119	Ir	3	0	Nb2 Iq1	-	-	-	-	-	OCH2CH2	H	-	-	H	H	H	H	-	-	-	-
120	Ir	3	0	Pe Iq1	-	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-

Table 7











No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
121	1	3	0	Pe	1q1	-	-	-	-	Ph	H	-	-	-	-	-	-	-	-
122	1	3	0	Pe	1q1	-	-	-	-		Ph	H	H	H	H	-	-	-	-
123	1	3	0	Pe	1q1	-	-	-	-	Ph	H	H	Ph	H	H	-	-	-	-
124	1	3	0	Pe	1q1	-	-	-	-	CH3	H	H	H	CF3	H	-	-	-	-
125	1	3	0	Pe	1q1	-	-	-	-	H	CH3	H	CF3	H	H	-	-	-	-
126	1	3	0	Pe	1q1	-	-	-	-		H	H	H	H	H	-	-	-	-
127	1	3	0	Pe	1q1	-	-	-	-	H		H	H	H	H	-	-	-	-
128	1	3	0	Pe	1q1	-	-	-	-		H	H	H	H	H	-	-	-	-
129	1	3	0	Pe	1q1	-	-	-	-	H		H	H	H	H	-	-	-	-
130	1	3	0	Pe	1q1	-	-	-	-	CF3	H	H	H	H	H	-	-	-	-
131	1	3	0	Pe	1q1	-	-	-	-	H	CF3	H	H	H	H	-	-	-	-
132	1	3	0	Pe	1q1	-	-	-	-		H	H	H	H	H	-	-	-	-
133	1	3	0	Pe	1q1	-	-	-	-	H		H	H	H	H	-	-	-	-
134	1	3	0	Pe	1q1	-	-	-	-		H	H	H	H	H	-	-	-	-
135	1	3	0	Pe	1q1	-	-	-	-		H	H	H	H	H	-	-	-	-
136	1	3	0	Pe	1q1	-	-	-	-	CH3	H	H	H	H	H	-	-	-	-
137	1	3	0	Pe	1q1	-	-	-	-	H	CH3	H	H	H	H	-	-	-	-
138	1	3	0	Pe	1q1	-	-	-	-		H	H	Ph	H	H	-	-	-	-
139	1	3	0	Pe	1q1	-	-	-	-	H	H	H	Ph	H	H	-	-	-	-
140	1	3	0	Pe	1q1	-	-	-	-	H	H	H	H	Ph	H	-	-	-	-

Table 8



No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
141	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	H		H	H	-	-	-	-
142	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	H	H		H	-	-	-	-
143	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
144	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
145	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	H	F	H	H	-	-	-	-
146	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	H	H	H	F	-	-	-	-
147	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	F	H	H	H	-	-	-	-
148	1	3	0	Pe	la1	-	-	-	-	H	H	-	-	H	H	F	H	-	-	-	-
149	1	3	0	Pe	la1	-	-	-	-	OCH2CH2	H	-	-	H	H	H	H	-	-	-	-
150	1	3	0	Cn1	la1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
151	1	3	0	Cn1	la1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
152	1	3	0	Cn1	la1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
153	1	3	0	Cn1	la1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
154	1	3	0	Cn1	la1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-
155	1	3	0	Cn1	la1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-
156	1	3	0	Cn1	la1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
157	1	3	0	Cn1	la1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
158	1	3	0	Cn1	la1	-	-	-	-	H	H	-	-	CF3	H	H	H	-	-	-	-
159	1	3	0	Cn1	la1	-	-	-	-	OCH3	H	-	-	H	H	H	CF3	-	-	-	-
160	1	3	0	Cn2	la1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-

Table 9






No	M	N	m	A	B	A'	B'	E	Q	A-R1	A-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
161	1	3	0	Cn2	1q1	-	-	-	-	Ph	H	-	H	H	H	-	-	-	-
162	1	3	0	Cn2	1q1	-	-	-	-	Ph	Ph	H	H	H	H	-	-	-	-
163	1	3	0	Cn2	1q1	-	-	-	-	Ph	H	H	Ph	H	H	-	-	-	-
164	1	3	0	Cn2	1q1	-	-	-	-	CH3	H	H	H	H	H	-	-	-	-
165	1	3	0	Cn2	1q1	-	-	-	-	H	CH3	H	H	H	H	-	-	-	-
166	1	3	0	Cn2	1q1	-	-	-	-	H	H	H	CF3	H	H	-	-	-	-
167	1	3	0	Cn2	1q1	-	-	-	-	H	H	H	H	CF3	H	-	-	-	-
168	1	3	0	Cn2	1q1	-	-	-	-	H	H	CF3	H	H	H	-	-	-	-
169	1	3	0	Cn2	1q1	-	-	-	-	OC-3	H	H	H	H	CF3	-	-	-	-
170	1	3	0	Fl	1q1	-	-	-	-	H	H	H	H	H	H	-	-	-	-
171	1	3	0	Fl	1q1	-	-	-	-	Ph	H	H	H	H	H	-	-	-	-
172	1	3	0	Fl	1q1	-	-	-	-		Ph	H	H	H	H	-	-	-	-
173	1	3	0	Fl	1q1	-	-	-	-	Ph	H	H	Ph	H	H	-	-	-	-
174	1	3	0	Fl	1q1	-	-	-	-	CH3	H	H	H	CF3	H	-	-	-	-
175	1	3	0	Fl	1q1	-	-	-	-	H	CH3	H	CF3	H	H	-	-	-	-
176	1	3	0	Fl	1q1	-	-	-	-		H	H	H	H	H	-	-	-	-
177	1	3	0	Fl	1q1	-	-	-	-	H		H	H	H	H	-	-	-	-
178	1	3	0	Fl	1q1	-	-	-	-		H	H	H	H	H	-	-	-	-
179	1	3	0	Fl	1q1	-	-	-	-	H		H	H	H	H	-	-	-	-
180	1	3	0	Fl	1q1	-	-	-	-	CF3	H	H	H	H	H	-	-	-	-

Table 10








No	M	N	m	A	B	A'	B'	E	Q	A-R1	A-R2	B-R3	B-R4	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
181	1	3	0	F1	1q1	-	-	-	-	H	CF3	H	H	H	-	-	-	-
182	1	3	0	F1	1q1	-	-	-	-		H	H	H	H	-	-	-	-
183	1	3	0	F1	1q1	-	-	-	-	H		H	H	H	-	-	-	-
184	1	3	0	F1	1q1	-	-	-	-		H	H	H	H	-	-	-	-
185	1	3	0	F1	1q1	-	-	-	-		H	H	H	H	-	-	-	-
186	1	3	0	F1	1q1	-	-	-	-	OCH3	H	H	H	H	-	-	-	-
187	1	3	0	F1	1q1	-	-	-	-	H	OCH3	H	H	H	-	-	-	-
188	1	3	0	F1	1q1	-	-	-	-		H	H	H	H	-	-	-	-
189	1	3	0	F1	1q1	-	-	-	-	H	H	H	H	H	-	-	-	-
190	1	3	0	F1	1q1	-	-	-	-	H	H	H	H	H	-	-	-	-
191	1	3	0	F1	1q1	-	-	-	-	H	H	H		H	-	-	-	-
192	1	3	0	F1	1q1	-	-	-	-	H	H	H	H		-	-	-	-
193	1	3	0	F1	1q1	-	-	-	-	H	H	H	CF3	H	-	-	-	-
194	1	3	0	F1	1q1	-	-	-	-	H	H	H	H	CF3	-	-	-	-
195	1	3	0	F1	1q1	-	-	-	-	H	H	H	F	H	-	-	-	-
196	1	3	0	F1	1q1	-	-	-	-	H	H	H	H	H	-	-	-	-
197	1	3	0	F1	1q1	-	-	-	-	H	H	F	H	H	-	-	-	-
198	1	3	0	F1	1q1	-	-	-	-	H	H	H	H	F	-	-	-	-
199	1	3	0	F1	1q1	-	-	-	-	OCH2CH2	H	H	H	H	-	-	-	-
200	1	3	0	Qn1	1q1	-	-	-	-	H	H	H	H	H	-	-	-	-



Table 11



No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
201	1	3	0	Cn1	1q1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
202	1	3	0	Cn1	1q1	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
203	1	3	0	Cn1	1q1	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
204	1	3	0	Cn1	1q1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-
205	1	3	0	Cn1	1q1	-	-	-	-	H	CH3	-	-	H	H	H	H	-	-	-	-
206	1	3	0	Cn1	1q1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
207	1	3	0	Cn1	1q1	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
208	1	3	0	Cn1	1q1	-	-	-	-	H	H	-	-	CF3	H	H	H	-	-	-	-
209	1	3	0	Cn1	1q1	-	-	-	-		H	-	-	H	H	H	CF3	-	-	-	-
210	1	3	0	Cn2	1q1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
211	1	3	0	Cn2	1q1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
212	1	3	0	Cn2	1q1	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
213	1	3	0	Cn2	1q1	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
214	1	3	0	Cn2	1q1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-
215	1	3	0	Cn2	1q1	-	-	-	-	H	CH3	-	-	H	H	H	H	-	-	-	-
216	1	3	0	Cn2	1q1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
217	1	3	0	Cn2	1q1	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
218	1	3	0	Cn2	1q1	-	-	-	-	H	H	-	-	CF3	H	H	H	-	-	-	-
219	1	3	0	Cn2	1q1	-	-	-	-		H	-	-	H	H	H	CF3	-	-	-	-
220	1	3	0	Cz	1q1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-

Table 12







No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	B-R1	B-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
221	1	3	0	Cz	1q1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
222	1	3	0	Cz	1q1	-	-	-	-	CH3	Ph	-	-	H	H	H	H	-	-	-	-
223	1	3	0	Cz	1q1	-	-	-	-	Ph	Ph	-	-	H	H	H	H	-	-	-	-
224	1	3	0	Cz	1q1	-	-	-	-	CH2CH3	H	-	-	H	H	H	H	-	-	-	-
225	1	3	0	Cz	1q1	-	-	-	-	CH3	CH3	-	-	H	H	H	H	-	-	-	-
226	1	3	0	Cz	1q1	-	-	-	-	CH3	H	-	-	H	CF3	H	H	-	-	-	-
227	1	3	0	Cz	1q1	-	-	-	-	CH3	H	-	-	H	H	CF3	H	-	-	-	-
228	1	3	0	Cz	1q1	-	-	-	-	CH3		-	-	H	H	H	H	-	-	-	-
229	1	3	0	Cz	1q1	-	-	-	-		Ph	-	-	H	H	H	CF3	-	-	-	-
230	1	3	0	Cz	1q1	-	-	-	-	Ph	Ph	-	-	H	H	Ph	H	-	-	-	-
231	1	3	0	Ph	1q2	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
232	1	3	0	Ph	1q2	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
233	1	3	0	Ph	1q2	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
234	1	3	0	Ph	1q2	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
235	1	3	0	Ph	1q2	-	-	-	-	CH3	H	-	-	H	H	CF3	H	-	-	-	-
236	1	3	0	Ph	1q2	-	-	-	-	H	CH3	-	-	H	CF3	H	H	-	-	-	-
237	1	3	0	Ph	1q2	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
238	1	3	0	Ph	1q2	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
239	1	3	0	Ph	1q2	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
240	1	3	0	Ph	1q2	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-

Table 13










No	M	N	m	A	B	A'	B'	E	Q	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
241	Y	3	0	Ph	1a2	-	-	-	-	CF3	H	-	-	H	H	H	H	-	-	-	-
242	Y	3	0	Ph	1a2	-	-	-	-	H	CF3	-	-	H	H	H	H	-	-	-	-
243	Y	3	0	Ph	1a2	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
244	Y	3	0	Ph	1a2	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
245	Y	3	0	Ph	1a2	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
246	Y	3	0	Ph	1a2	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
247	Y	3	0	Ph	1a2	-	-	-	-	OCH3	H	-	-	H	H	H	H	-	-	-	-
248	Y	3	0	Fl	1a1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
249	Y	3	0	Ph	1a2	-	-	-	-		H	-	-	H	Ph	H	H	-	-	-	-
250	Y	3	0	Ph	1a3	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
251	Y	3	0	Ph	1a3	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
252	Y	3	0	Ph	1a3	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
253	Y	3	0	Ph	1a3	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
254	Y	3	0	Ph	1a3	-	-	-	-	CH3	H	-	-	H	H	CF3	H	-	-	-	-
255	Y	3	0	Ph	1a3	-	-	-	-	H	CH3	-	-	H	CF3	H	H	-	-	-	-
256	Y	3	0	Ph	1a3	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
257	Y	3	0	Ph	1a3	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
258	Y	3	0	Ph	1a3	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
259	Y	3	0	Ph	1a3	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
260	Y	3	0	Ph	1a3	-	-	-	-	CF3	H	-	-	H	H	H	H	-	-	-	-

Table 14


No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
261	Y	3	0	Ph	Iq3	-	-	-	-	-	CF3	H	H	H	H	-	-	-	-
262	Y	3	0	Ph	Iq3	-	-	-	-	-	H	H	H	H	H	-	-	-	-
263	Y	3	0	Ph	Iq3	-	-	-	-	-		H	H	H	H	-	-	-	-
264	Y	3	0	Ph	Iq3	-	-	-	-	-	H	H	H	H	H	-	-	-	-
265	Y	3	0	Ph	Iq3	-	-	-	-	-	H	H	H	H	H	-	-	-	-
266	Y	3	0	Ph	Iq3	-	-	-	-	-	H	H	H	H	H	-	-	-	-
267	Y	3	0	Ph	Iq3	-	-	-	-	-	OCH3	H	H	H	H	-	-	-	-
268	Y	3	0	Ph	Iq3	-	-	-	-	-	H	H	H	H	H	-	-	-	-
269	Y	2	1	Ph	Iq1	Ph	Pr	-	-	-	H	H	H	H	H	-	-	-	-
270	Y	2	1	Ph	Iq1	Tn3	Pr	-	-	-	H	H	H	H	H	-	-	-	-
271	Y	2	1	Ph	Iq1	Tn3	Pr	-	-	-	OCH3	H	H	H	H	-	-	-	-
272	Y	2	1	Ph	Iq1	Np2	Pr	-	-	-	H	H	H	H	H	-	-	-	-
273	Y	2	1	Ph	Iq1	Fl	Pr	-	-	-	H	H	H	H	H	-	-	-	-
274	Y	2	1	Ph	Iq1	-	-	-	CF3	-	H	H	H	H	H	-	-	-	-
275	Y	2	1	Ph	Iq1	-	-	-	C2H5	-	H	H	H	H	H	-	-	-	-
276	Y	2	1	Ph	Iq1	-	-	-	CH3	-	H	H	H	H	H	-	-	-	-
277	Y	2	1	Ph	Iq1	-	-	-	Ph	-	H	H	H	H	H	-	-	-	-
278	Y	2	1	Tn1	Iq1	Tn3	Pr	-	-	-	CH3	H	H	H	H	-	-	-	-
279	Y	2	1	Tn1	Iq1	Pa	Pr	-	-	-	H	H	H	H	H	-	-	-	-
280	Y	2	1	Tn1	Iq1	-	-	-	CH3	-	H	H	H	H	H	-	-	-	-

Table 15

No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A-R1	A-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
281	✓	2	1	Tn1	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
282	✓	2	1	Tn1	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
283	✓	2	1	Tn2	Iq1	Tn3	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
284	✓	2	1	Tn2	Iq1	Tn3	Pr	—	—	H	H	H	H	H	H	H	H	—	—	—	—
285	✓	2	1	Tn2	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
286	✓	2	1	Tn2	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
287	✓	2	1	Tn2	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	CF3	—	—	—
288	✓	2	1	Tn3	Iq1	Ph	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
289	✓	2	1	Tn3	Iq1	Ph	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
290	✓	2	1	Tn3	Iq1	Ph	Iq1	—	—	H	H	H	H	H	H	H	H	H	H	H	—
291	✓	2	1	Tn3	Iq1	Tn1	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
292	✓	2	1	Tn3	Iq1	Tn2	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
293	✓	2	1	Tn3	Iq1	Np2	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
294	✓	2	1	Tn3	Iq1	Np3	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
295	✓	2	1	Tn3	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
296	✓	2	1	Tn3	Iq1	—	—	C2H5	C2H5	H	H	—	—	H	H	H	H	—	—	—	—
297	✓	2	1	Tn3	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
298	✓	2	1	Tn3	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
299	✓	2	1	Tn3	Iq1	—	—	OCH3	OCH3	H	H	—	—	H	H	H	H	—	—	—	—
300	✓	2	1	Tn3	Iq1	—	—	CH3	Ph	H	H	—	—	H	H	H	H	—	—	—	—

Table 16

No	M	N	m	A	B	A'	B'	E	Q	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
301	1	2	1	Tn3	Iq1	—	—	NPh2	NPh2	H	H	—	—	H	H	H	H	—	—	—	—
302	1	2	1	Tn3	Iq1	—	—	CH3	NPh2	H	H	—	—	H	H	H	H	—	CF3	—	—
303	1	2	1	Np1	Iq1	Tn3	Pr	—	—	H	H	H	H	H	H	H	H	H	Ph	—	—
304	1	2	1	Np1	Iq1	Tn3	Pr	—	—	H	H	H	H	H	H	H	H	—	—	—	—
305	1	2	1	Np1	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
306	1	2	1	Np1	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
307	1	2	1	Np1	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
308	1	2	1	Np2	Iq1	Ph	Pr	—	—	H	H	H	H	H	H	H	H	H	Ph	—	—
309	1	2	1	Np2	Iq1	Ph	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
310	1	2	1	Np2	Iq1	Ph	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
311	1	2	1	Np2	Iq1	Tn1	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
312	1	2	1	Np2	Iq1	Tn3	Pr	—	—	H	H	H	H	H	H	H	H	H	CF3	—	—
313	1	2	1	Np2	Iq1	Np2	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
314	1	2	1	Np2	Iq1	Np3	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
315	1	2	1	Np2	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
316	1	2	1	Np2	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
317	1	2	1	Np2	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
318	1	2	1	Np2	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
319	1	2	1	Np2	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
320	1	2	1	Np2	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—

Table 17

No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
321	✓	2	1	Ne2	Iq1	—	—	NPh2	NPh2	H	H	—	—	H	H	H	H	—	—	—	—
322	✓	2	1	Ne2	Iq1	—	—	CH3	NPh2	H	H	H	H	H	H	H	H	H	H	—	—
323	✓	2	1	Pe	Iq1	Ph	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
324	✓	2	1	Pe	Iq1	Ph	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
325	✓	2	1	Pe	Iq1	Tn1	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
326	✓	2	1	Pe	Iq1	Tn3	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
327	✓	2	1	Pe	Iq1	Ne2	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
328	✓	2	1	Pe	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
329	✓	2	1	Pe	Iq1	—	—	C2H5	C2H5	H	H	—	—	H	H	H	H	—	—	—	—
330	✓	2	1	Pe	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
331	✓	2	1	Pe	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
332	✓	2	1	Pe	Iq1	—	—	NPh2	NPh2	H	H	—	—	H	H	H	H	—	—	—	—
333	✓	2	1	Cn1	Iq1	Tn3	Pr	—	—	H	CH3	H	H	H	H	H	H	H	H	—	—
334	✓	2	1	Cn1	Iq1	Pe	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
335	✓	2	1	Cn1	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
336	✓	2	1	Cn1	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
337	✓	2	1	Cn1	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
338	✓	2	1	Cn2	Iq1	Tn3	Pr	—	—	H	CH3	H	H	H	H	H	H	H	H	—	—
339	✓	2	1	Cn2	Iq1	Pe	Pr	—	—	H	H	H	H	H	H	H	H	H	H	—	—
340	✓	2	1	Cn2	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—

Table 18




No	M	N	E	A	B	A'	B'	E	Q	A-R1	A-R2	A-R1	A-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
341	1	2	1	Gn2	1q1	-	-	Ph	Ph	H	H	-	-	H	H	H	H	-	-	-	-
342	1	2	1	Gn2	1q1	-	-	CF3	CF3	H	H	-	-	H	H	H	H	-	-	-	-
343	1	2	1	Fl	1q1	Ph	Ph	-	-	H	H	H	H	H	H	H	H	H	H	-	-
344	1	2	1	Fl	1q1	Ph	Ph	-	-	H	H	H	H	H	H	H	H	H	H	-	-
345	1	2	1	Fl	1q1	Tn1	Ph	-	-	H	H	H	H	H	H	H	H	H	H	-	-
346	1	2	1	Fl	1q1	Tn3	Ph	-	-	H	H	H	H	H	H	H	H	H	H	-	-
347	1	2	1	Fl	1q1	Ph	Ph	-	-	H	H	H	H	H	H	H	H	H	H	-	-
348	1	2	1	Fl	1q1	Tn3	Ph	-	-	H	H	H	H	H	H	H	H	H	H	-	-
349	1	2	1	Fl	1q1	Tn3	Ph	-	-	H	H	H	H	H	H	H	H	H	H	-	-
350	1	2	1	Fl	1q1	-	-	CF3	CF3	H	H	-	-	H	H	H	H	-	-	-	-
351	1	2	1	Fl	1q1	-	-	C2H5	C2H5	H	H	-	-	H	H	H	H	-	-	-	-
352	1	2	1	Fl	1q1	-	-	CH3	CH3	H	H	-	-	H	H	H	H	-	-	-	-
353	1	2	1	Fl	1q1	-	-	Ph	Ph	H	H	-	-	H	H	H	H	-	-	-	-
354	1	2	1	Fl	1q1	-	-	OCH3	OCH3	H	H	-	-	H	H	H	H	-	-	-	-
355	1	2	1	Fl	1q1	-	-	CH3	Ph	H	H	-	-	H	H	H	H	-	-	-	-
356	1	2	1	Fl	1q1	-	-	NPh2	NPh2	H	H	-	-	H	H	H	H	-	-	-	-
357	1	2	1	Fl	1q1	-	-	CH3	NPh2	H	H	-	-	H	H	H	H	-	-	-	-
358	1	2	1	Gn1	1q1	Tn3	Ph	-	-	H	H	H	H	H	H	H	H	H	CF3	-	-
359	1	2	1	Gn1	1q1	Tn3	Ph	-	-	H	H	H	H	H	H	H	H	H	Ph	-	-
360	1	2	1	Gn1	1q1	-	-	CH3	CH3	H	H	-	-	H	H	H	H	-	-	-	-



Table 19

No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A'-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
381	✓	2	1	Gn1	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
382	✓	2	1	Gn1	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
383	✓	2	1	Gn2	Iq1	Tr3	—	—	—	H	H	H	H	H	H	H	H	H	CF3	—	—
384	✓	2	1	Gn2	Iq1	Tr3	—	—	—	H	H	H	H	H	H	H	H	H	Ph	—	—
385	✓	2	1	Gn2	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
386	✓	2	1	Gn2	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
387	✓	2	1	Gn2	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
388	✓	2	1	Cz	Iq1	Tr3	—	—	—	H	H	H	H	H	H	H	H	H	CF3	—	—
389	✓	2	1	Cz	Iq1	Tr3	—	—	—	H	H	H	H	H	H	H	H	H	Ph	—	—
390	✓	2	1	Cz	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
391	✓	2	1	Cz	Iq1	—	—	Ph	Ph	H	H	—	—	H	H	H	H	—	—	—	—
392	✓	2	1	Cz	Iq1	—	—	CF3	CF3	H	H	—	—	H	H	H	H	—	—	—	—
393	Rh	3	0	Ph	Iq1	—	—	—	—	H	H	—	—	H	H	H	H	—	—	—	—
394	Rh	3	0	Ph	Iq1	—	—	—	—	Ph	H	—	—	H	H	H	H	—	—	—	—
395	Rh	3	0	Ph	Iq1	—	—	—	—	H	H	—	—	H	H	H	H	—	—	—	—
396	Rh	3	0	Ph	Iq1	—	—	—	—	Ph	H	—	—	H	H	H	H	—	—	—	—
397	Rh	3	0	Ph	Iq1	—	—	—	—	Ph	H	—	—	H	H	H	H	—	—	—	—
398	Rh	3	0	Ph	Iq1	—	—	—	—	CH3	H	—	—	H	H	H	H	—	—	—	—
399	Rh	3	0	Ph	Iq1	—	—	—	—	H	CH3	—	—	H	H	H	H	—	—	—	—
400	Rh	2	1	Ph	Iq1	—	—	CH3	CH3	H	H	—	—	H	H	H	H	—	—	—	—
401	Ph	2	0	Ph	Iq1	—	—	—	—	H	H	—	—	H	H	H	H	—	—	—	—

Table 20

No	M	N	m	A	B	A'	B'	E	G	A-R1	A-R2	A-R1	A'-R2	B-R3	B-R4	B-R5	B-R6	B'-R3	B'-R4	B'-R5	B'-R6
381	Pt	2	0	Ph	lq1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
382	Pt	2	0	Ph	lq1	-	-	-	-	Ph	Ph	-	-	H	H	H	H	-	-	-	-
383	Pt	2	0	Ph	lq1	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
384	Pt	2	0	Ph	lq1	-	-	-	-	CH3	H	-	-	H	H	CF3	H	-	-	-	-
385	Pt	2	0	Ph	lq1	-	-	-	-	H	CH3	-	-	H	CF3	H	H	-	-	-	-
386	Pt	2	0	Ph	lq1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
387	Pt	2	0	Ph	lq1	-	-	-	-	H		-	-	H	H	H	H	-	-	-	-
388	Pt	2	0	Ph	lq1	-	-	-	-		H	-	-	H	H	H	H	-	-	-	-
389	Pt	2	0	Tn1	lq1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
390	Pt	2	0	Ph	lq2	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
391	Pt	2	0	Ph	lq2	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
392	Pt	2	0	Tn1	lq1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
393	Pt	2	0	Tn1	lq1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
394	Pt	2	0	Tn1	lq1	-	-	-	-	H	CH3	-	-	H	Ph	H	H	-	-	-	-
395	Pt	2	0	Tn1	lq1	-	-	-	-	CH3	H	-	-	H	H	H	H	-	-	-	-
396	Pt	2	0	Tn1	lq1	-	-	-	-	H	CH3	-	-	H	H	H	H	-	-	-	-
397	Pt	2	0	Tn1	lq1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
398	Pt	2	0	Tn1	lq1	-	-	-	-	H	H	-	-	H	CF3	H	H	-	-	-	-
399	Pt	2	0	Tn1	lq1	-	-	-	-	H	H	-	-	H	H	CF3	H	-	-	-	-
400	Pt	2	0	Tn1	lq1	-	-	-	-	H	H	-	-	CF3	H	H	H	-	-	-	-
401	Pd	2	0	Ph	lq1	-	-	-	-	H	H	-	-	H	H	H	H	-	-	-	-
402	Pd	2	0	Ph	lq1	-	-	-	-	Ph	H	-	-	H	H	H	H	-	-	-	-
403	Pd	2	0	Ph	lq1	-	-	-	-	H	Ph	-	-	H	H	H	H	-	-	-	-
404	Pd	2	0	Ph	lq1	-	-	-	-	Ph	H	-	-	H	Ph	H	H	-	-	-	-
405	Pd	2	0	Ph	lq1	-	-	-	-	CH3	H	-	-	H	H	CF3	H	-	-	-	-
406	Pd	2	0	Ph	lq1	-	-	-	-	H	CH3	-	-	H	CF3	H	H	-	-	-	-
407	Pd	1	1	Ph	lq1	Ph	Ph	-	-	H	H	-	-	H	H	H	H	-	-	-	-

[Examples]

Hereinafter, the present invention will be described more specifically based on Examples.

<Examples 1 - 2>

The structure including four organic layers as shown in Figure 1 was prepared as the structure of the device. The opposing electrode area is made into  $3 \text{ mm}^2$  by patterning a 100 nm-thick film (transparent substrate 14) of ITO on a glass substrate (transparent substrate 15). On the ITO-formed substrate, three organic layers and two metal electrode layers shown below were successively formed by vacuum (vapor) deposition using resistance heating in a vacuum chamber ( $10^{-4}$  Pa).

Organic layer 1 (hole transport layer 13)  
(40 nm):  $\alpha$ -NPD

Organic layer 2 (luminescence layer 12) (30 nm): co-deposited film of CBP: metal complex (metal coordination compound) (8 wt. %)

Organic layer 3 (electron transport layer 16) (30 nm): Alq3

Metal electrode layer 1 (metal electrode 11)  
(15 nm): Al-Li alloy (Li = 1.8 wt. %)

Metal electrode layer 2 (metal electrode 11)  
(100 nm): Al

As the ligands, Example Compound No. 1, 170 was used.

The performances of the thus-obtained EL devices were measured by using a micro-current meter ("4140B", made by Hewlett-Packard Corp.) for a current-voltage characteristic and "BM7" (made by Topcon K.K.) for an emission luminance. The devices using the respective coordination compounds respectively exhibited a good rectifying characteristic.

At an applied voltage of 12 volts, the EL devices exhibited luminescence as follows:

Device of Example 1 (Compound No. 1):

8000 cd/cm<sup>2</sup>

Device of Example 2 (Compound No. 28):

1000 cm/m<sup>2</sup>

The above-mentioned luminescence of the EL device almost coincide with the photoluminescence measured by dissolving the luminescence material used in this embodiment in toluene, whereby it was confirmed that the luminescence of the EL device were emitted from the above-mentioned luminescence material.

<Examples 3 - 7, Comparative Example 1>

Luminescence devices were prepared in the same manner as in Examples 1 and 2 except for using luminescence materials (Example Compounds) shown in Table 26 below. In Comparative Example 1, the above-mentioned Ir(ppy)<sub>3</sub> represented by Ka-3 was used as a representative of conventional luminescence material.

The measurement results of a current conduction durability test for each luminescence devices are shown in Table 26 and the Example materials exhibited a luminance half-attenuation period which was clearly longer than the conventional luminescence material, thus providing a device having a high durability attributable to the material of the present invention.

Table 21

	Luminescence material No.	Luminance half-attenuation period (hours)
Ex. 3	1	700
Ex. 4	51	490
Ex. 5	91	800
Ex. 6	120	850
Comp. 1	170	900
Comp. 2	Ir(ppy) <sub>3</sub>	350

<Example 8>

A simple matrix type organic EL device as shown in Figure 2 was prepared in the following manner.

On a glass substrate 21 measuring 75 mm-length, 75 mm-width and 1.1 mm-thickness, a ca. 100 nm-thick ITO film was formed by sputtering and

patterned into 100 lines of 100  $\mu\text{m}$ -wide transparent electrodes 22 (anode side) with a spacing of 40  $\mu\text{m}$  as simple matrix electrodes. Then, formed layers of identical organic materials were found under identical conditions as in Example 2 to form an organic compound layer 23.

Then, 100 lines of 100  $\mu\text{m}$ -wide Al electrodes 24 were formed with a spacing of 40  $\mu\text{m}$  by mask vacuum deposition so as to be perpendicular to the transparent electrodes 22 by vacuum deposition at a vacuum of  $2.7 \times 10^{-3}$  Pa ( $2 \times 10^{-5}$  Torr). The metal electrodes (cathode) 24 were formed as a lamination of 10 nm-thick layer of Al/Li alloy (Li: 1.3 wt. %) and then 150 nm-thick layer of Al.

The thus-obtained 100x100-simple matrix-type organic EL device was subjected to a simple matrix drive in a glove box filled with nitrogen at voltages of 7 volts to 13 volts by using a scanning signal of 10 volts and data signals of  $\pm 3$  volts. As a result of an interlaced drive at a frame efficiency of 30 Hz, respectively, luminescence images could be confirmed. [Advantageous Effect]

As described in foregoing, according to the present invention, a luminescence device of the present invention using, as a principle luminescence material, a metal coordination compound of the formula (1) is an excellent device which not only allows high

luminescence efficiency at a high brightness (or luminance) for a long period while increasing the luminescence wavelength. Further, the display apparatus which exhibits an excellent display performance of the image by using the luminescence device of the present invention.

[Brief Description of the Drawings]

Figures 1A, 1B and 1C are schematic sectional views of an embodiment of a luminescence device according to the present invention, respectively.

Figure 2 illustrates a simple matrix-type organic EL device according to Example 8.

Figure 3 illustrates drive signals used in Example 8.

Figure 4 schematically illustrates a panel structure including an EL device and drive means.

Figure 5 is a schematic view of an example of a pixel electrode.

Figure 6 illustrates an embodiment of a sectional structure of TFT (thin-film transistor) substrate.

[Reference Numerals]

- 11: metal electrode
- 12: luminescence layer
- 13: hole transfer layer
- 14: transparent electrode

- 15: transparent substrate
- 16: electron transport layer
- 17: exciton diffusion-prevention layer
- 21: glass substrate
- 22: ITO electrode (transparent electrode)
- 23: organic compound layer
- 24: cathode



FIG. 1






FIG. 2




FIG. 3




FIG. 4




FIG. 5





FIG. 6



[Document]

Abstract

[Abstract]

[Object]

It is a principal object of the present invention to provide a luminescence device which exhibits a high luminescence efficiency and have a luminescence wavelength of long-wavelength region, and retains a high luminance for a long period.




[Means for Solving]

There is provided a luminescence device having a layer containing a metal coordination compound, which is represented by formula (1) below:



wherein M is a metal atom of Ir, Pt, Rh or Pd; L and L' are mutually different bidentate ligands; m is 1, 2 or 3 and n is 0, 1 or 2 with the proviso that m+n is 2 or 3; a partial structure ML<sub>m</sub> is represented by formula (2) shown below and a partial structure ML'<sub>n</sub> is represented by formula (3) or (4) shown below:

<KA-1>



[Selected Figure]

Figure 1